

## **BIOFA Hartwachs lösemittelhaltig (Hard Wax, solvent-based) Art. No. 2060**

### **Properties**

BIOFA Hartwachs is a protective and care product for wood, cork, linoleum, stone surfaces, etc. inside. It is easy to use, colourless, water-repellent, moisture-vapour permeable and has a pleasant, mild odour. The finish is silk gloss, hard wearing and antistatic. Suitable for all hard- and soft-wood that is untreated, smooth or has been pretreated with wax, stain or oil. Especially recommended for floors, furniture, interior fittings, toys, antiques, etc. Do not use in damp rooms or in splash water areas.

### **Ingredients**

Aliphatic hydrocarbons, beeswax, carnauba wax, paraffin wax, citral.

### **Instructions for use:**

#### **1. Pretreatment**

Substrates must be finely sanded, dry (max. 12% wood moisture) and clean. If necessary, clean with BIOFA Verdünnung (Thinner) 0500. Prime highly absorptive substrates with Universal Hartgrund (Universal Hard Primer) 3755 (carry out intermediate sanding).

#### **2. Application**

BIOFA Hartwachs is ready for use. Apply a wafer-thin layer evenly with a lint-free cloth or mechanically, distribute avoiding streaks and polish. Wait for 3-6 hours and polish again manually or mechanically. Apply a second wax layer to highly stressed surfaces.

**Important! Carry out preliminary tests!  
Provide optimum fresh air circulation  
during product application and drying!  
Do not use under 16°C!**

#### **3. Cleaning of tools**

Clean with Verdünnung (Thinner) 0500 immediately after use.

#### **4. Cleaning and maintenance of surfaces**

Dry cleaning with a soft broom, cloth, mop or vacuum cleaner brush. For damp cleaning, use pH-neutral, mild cleaner in hand-hot water. We recommend NACASA Universalreiniger (Universal Cleaner) 4010 (BIOFA dealer). See special maintenance instructions for floor surfaces!

#### **Drying**

Dry, polishable and resistant to minor stress after 3-6 hours (20°C/ 50-55% rel. air humidity). Fully stress-resistant after 24 hours.

#### **Consumption/spreading rate per coat**

Crude wood: 25-35g/m<sup>2</sup> or 30-40m<sup>2</sup>/l  
Primed wood: 15-20g/m<sup>2</sup> or 50-70m<sup>2</sup>/l  
Wax machine: 8-10g/m<sup>2</sup> or 100-125m<sup>2</sup>/l

#### **Storage**

Cool, dry and sealed airtight.

#### **Container size**

200 ml / 1 l / 2.5 l metal containers.

#### **Safety instructions**

Keep out of reach of children. Do not inhale vapour/aerosol. Only use in well-ventilated areas. Contains citral. Can cause allergic reactions. When heating or spraying, explosive vapour/air mixtures can be generated! Wear adequate skin protection when using! There may be an odour typical of the natural raw materials!

#### **Disposal**

Dispose of large amounts of pasty product residue at collection points for old paints/varnishes or dispose of according to locally applicable regulations. Small quantities of residue and soaked work materials

The data and information provided in this technical data sheet are binding. If it is necessary to deviate from these provisions, the Application Technology Department of BIOFA must be consulted in advance. The general rules for structural engineering are to be complied with. With publication of this technical data sheet all previous data sheets regarding this product are no longer valid.

can be disposed of along with domestic waste after drying. Only recycle cleaned or completely empty packaging with cured deposits or dispose of according to locally applicable legal regulations. Uncleanable packaging and packaging not emptied appropriately must be treated and disposed of like the product!

**VOC identification according to Decopaint Directive and ChemVOCFarbV (Directive on the limitation of emissions of volatile organic compounds due to the use of organic solvents in paints and varnishes):**

EU limit value (cat. A/f): 700 g/l (2010)  
2060 contains max. 580 g/l VOC.

Waste Incineration Ordinance[AVV]-  
Waste Code according to European Waste Catalogue: 08 01 11\*

GISCODE: Ö 60

The data and information provided in this technical data sheet are binding. If it is necessary to deviate from these provisions, the Application Technology Department of BIOFA must be consulted in advance. The general rules for structural engineering are to be complied with. With publication of this technical data sheet all previous data sheets regarding this product are no longer valid.